

WHAT IS CLAIMED IS:

1. A method for manufacturing a lithographic printing plate, the method comprising:

a drying and heating step wherein, while a strip-shaped support, on which a photosensitive coating solution containing an organic solvent is coated such that a photosensitive coated layer is formed by the photosensitive coating solution, is continuously conveyed, the photosensitive coated layer is dried by a first heating means to a dry-to-touch state, and the support and the photosensitive coated layer are heated by a second heating means provided at a downstream side of the first heating means so that hardening of the photosensitive coated layer is promoted.

2. A method for manufacturing a lithographic printing plate according to claim 1, wherein the first heating means is a drying step in which the photosensitive coated layer is heated to 90°C or more.

3. A method for manufacturing a lithographic printing plate according to claim 1, wherein the first heating means is a drying step in which a remaining amount of the organic solvent in the photosensitive coated layer is 5 wt% or less of the photosensitive coated layer which is substantially completely dried.

4. A method for manufacturing a lithographic printing plate according to

claim 1, wherein a heating system of the first heating means is a hot air drying system.

5. A method for manufacturing a lithographic printing plate according to claim 1, wherein a heating system of the second heating means is a heat radiation system.

6. A method for manufacturing a lithographic printing plate according to claim 1, wherein a heating system of the second heating means is an induction heating system

7. A method for manufacturing a lithographic printing plate according to claim 1, wherein the support is one of a polyester film and an aluminum plate.

8. A method for manufacturing a lithographic printing plate according to claim 7, wherein a thickness of the aluminum plate is about 0.1 mm to 0.6 mm.

9. A method for manufacturing a lithographic printing plate according to claim 1, wherein a condition of heating by the second heating means is controlled in accordance with a type of the photosensitive coated layer formed on the support, such that a temperature of the photosensitive coated layer immediately after heating by the second heating means is a predetermined temperature which is set in accordance with the type of the

photosensitive coated layer.

10. A method for manufacturing a lithographic printing plate according to claim 9, wherein the lithographic printing plate is a thermal type digital direct printing plate, and a final temperature reached by the photosensitive coated layer is 125 to 145°C.

11. A method for manufacturing a lithographic printing plate according to claim 9, wherein the lithographic printing plate is a photopolymer type digital direct printing plate, and a final temperature reached by the photosensitive coated layer is 100 to 135°C.

12. A method for manufacturing a lithographic printing plate according to claim 1, wherein in a case in which thicknesses and widths of supports supplied to the second heating means continuously change, a condition of heating the supports and photosensitive coated layers by the second heating means changes in accordance with the thicknesses and the widths of the supports.

13. A method for manufacturing a lithographic printing plate according to claim 12, wherein the second heating means is a plurality of drying devices which are disposed along a conveying path of the support, and amounts of heat supplied by the plurality of heating devices are respectively controlled in accordance with changes in dimensions of the supports.

09895264.070201
102020 19256860

14. A method for manufacturing a lithographic printing plate according to claim 1, wherein after hot air drying of the coated layer by the first heating means, the second heating means radiates mid-infrared radiation or far infrared radiation to the photosensitive coated layer and the support so as to heat the support and the photosensitive coated layer.

15. A method for manufacturing a lithographic printing plate according to claim 1, further comprising a cooling step in which the support and the photosensitive coated layer are forcibly cooled by a cooling means provided at a downstream side of the second heating means.

16. A method for manufacturing a lithographic printing plate according to claim 15, wherein the cooling step is an air-cooling system in which low temperature air is blown out toward the photosensitive coated layer.

17. A method for manufacturing a lithographic printing plate according to claim 15, further comprising, at a downstream side of the cooling step, a step of forming an overcoat layer on the photosensitive coated layer.

add
a57